



PINK C

Applied to clear glass, the transparent Pink C film bestows a pink tint to the glass without diminishing its transparent properties. It is the perfect way to enliven any interior glazing (such as partitions, shower screens, etc.) with a touch of colour.



SOLAR SCREEN® Warranty
5 YEARS



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

WIDTHS AVAILABLE:

↔ **152 cm**

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	5 %
Visible light transmission	53 %
Reflection of external visible light	10 %
Reflection of internal visible light	10 %
Total solar energy rejected	19 %
Total solar energy rejected 2*	17 %
Solar ratio :	
Solar energy reflection	10 %
Solar energy absorption	37 %
Solar energy transmission	53 %
Reduction in Solar Glare	50 %
g-value	NC
u-value	NC
Shading coefficient	
Installation type : Interior	
Roll length	30,5 m
Film composition	PET
Thickness	40 µ

Colour from the outside : PINK

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. Dyed polyester without optical distortion
3. PS adhesive, glass polymerization within 15 days
4. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time. Consult our guarantee vouchers and our general conditions of sale.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	!

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.