



SPECTRA 333 XC

Ultimate evolution of the external Spectra series, nano ceramic base for recall, avoiding interference with electrical devices while providing a high level of infrared protection, which improves here its construction, providing best of class warranty.



SOLAR SCREEN® Warranty
See the notice "new guarantees for the external films"



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

WIDTHS AVAILABLE:

↔ **152 cm**

↔ **182 cm**

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	<1 %
Visible light transmission	75 %
Reflection of external visible light	8 %
Reflection of internal visible light	8 %
Total solar energy rejected	56 %
Total solar energy rejected 2*	59 %
Solar ratio :	
Solar energy reflection	6 %
Solar energy absorption	53 %
Solar energy transmission	41 %
Reduction in Solar Glare	29 %
g-value	0,49
u-value	5,08
Rejected Infrared (760-2500 nm)	95
Shading coefficient	0,6
Installation type : Exterior	
Roll length	30,5 m
Film composition	PET
Thickness	75 µ

Colour from the outside : HIGHLY NEUTRAL

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester with anti IR
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, SOLAR SCREEN® reserves the right to modify the composition of its films at any time. Consult our guarantee vouchers and our general conditions of sale.

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	✓
Tinted single pane	!
Reflective tinted single pane	✓
Clear double pane	!
Tinted double pane	!
Reflective tinted double pane	✓
Gas-filled double pane - Low E	!
STADIP EXT. clear double pane	✗
STADIP INT. clear double pane	!

✓ Yes ! Caution ✗ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal shock analysis report.