



WHITEBOARD

This PET-based film transforms your smooth or glass surfaces into an erasable whiteboard. Moreover, its regular and white back allows to be applied on glass partition, without unsightly effects



SOLAR SCREEN® Warranty
10 YEARS



Fire-resistance rating



Storage from -5°C to +40°C **3 YEARS**



REACH RoHS compliant

RESPECTED

WIDTHS AVAILABLE:



152 cm

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	8 %
Reflection of external visible light	80 %
Reflection of internal visible light	80 %
Total solar energy rejected	75 %
Total solar energy rejected 2*	70 %
Solar ratio:	
Solar energy reflection	59 %
Solar energy absorption	28 %
Solar energy transmission	13 %
Reduction in Solar Glare	91 %
g-value	0.20
u-value	5
Shading coefficient	0.1
Installation type: Interior	
Roll length	30,5 m
Film composition	PET
Thickness	100μ

Colour from the outside: WHITE

CONSTRUCTION

- 1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
- 2. Dyed polyester
- **3.** Bonding adhesive
- **4.** Dyed polyester
- **5.** PŠ adhesive, glass polymerization within 15 days
- **6.** Protection release liner, disposable after installation

MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 0805 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

 $Non-contractual\ data, SOLAR\ SCREEN @\ reserves\ the\ right\ to\ modify\ the\ composition\ of\ its\ films\ at\ any\ time.\ Consult\ our\ guarantee\ vouchers\ and\ our\ general\ conditions\ of\ sale.$

INSTALLATION ADVICE

Vertical installation and on standard glass surface**

Clear single pane	V
Tinted single pane	!
Reflective tinted single pane	V
Clear double pane	!
Tinted double pane	×
Reflective tinted double pane	~
Gas-filled double pane - Low E	×
STADIP EXT. clear double pane	×
STADIP INT. clear double pane	×

✓ Yes ! Caution ➤ Not recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.